

GRADATION REQUIREMENTS			
Percent Smaller			
Size, mm	Revetment	Class 1	Class 2
750			100
600		100	85-100
450	100	85-100	60-80
300	90-100	35-50	20-40
150	20-40	10-30	0-20
75	0-10	0-10	0-10
Minimum Depth of Riprap	450 mm	600 mm	750 mm

Note: The material shall be coarse aggregate, Class F or higher. It shall be in accordance with the above requirements and such that the maximum dimension of individual pieces shall not be greater than three times the minimum dimension. See Section 904 of the Standard Specifications for more information.

RIPRAP GRADATION REQUIREMENTS
Figure 38-61